



The Asphaltic Coating provides excellent adhesion, moisture resistance, limited protection for bare iron surfaces and is mostly used as a surface sealant.

Material

Asphaltic coating per ANSI/AWWA C104/A21.4, NSF-61 & 372
Modified Asphaltic Emulsion, Waterborne Safe, Single Component

Requirements

NSF-61 & 372, ANSI/AWWA C110/A21.10, ANSI/AWWA C111/A21.11, ANSI/AWWA C153/A21.53

Technical Data

Color: Black

Gloss: Semigloss - non-tacky

Application: Spray

Film Thickness: Wet:5 mils Dry: 3 mils

Dry Time @ 70°F: 10 min (non-tacky)

Minimum Dry Time: 7 Days

(for Potable Water)

Solids: 60-63%

VOCs: 0-VOC Free

HAPs: 0 - HAP Free

Odor: None

Flash Point: None

Specific Gravity 20°C: 1.03 -1.3