ASPHALT COATING

Technical Data

ELECTROSTEEL USA

The Asphaltic Coating provides excellent adhesion, moisture resistance, limited protection for bare iron surfaces and is mostly used as a surface sealant.

MATERIAL

Asphaltic coating per ANSI/AWWA C104/A21.4, NSF-61 & 372
Modified Asphaltic Emulsion, Waterborne Safe, Single Component

REQUIREMENTS

NSF-61 & 372, ANSI/AWWA C110/A21.10, ANSI/AWWA C111/A21.11, ANSI/AWWA C153/A21.53

TECHNICAL DATA

PROPERTY	VALUE
Color	Black
Gloss	Semigloss - non-tacky
Application	Spray
Film Thickness	Wet: 5 mils | Dry: 3 mils
Dry Time @ 70°F	10 min (non-tacky)
Minimum Dry Time (for Potable Water)	7 Days
Solids	60-63%
VOCs	0 - VOC Free
HAPs	0 - HAP Free
Odor	None
Flash Point	None
Specific Gravity 20°C	1.03 - 1.3

421 Telfair Rd | Savannah, GA 31415 | P: 912-387-0613 | Fax: 912-385-0315